

## PRODUCT DATA SHEET

# Sikaflex® Construction

Sealant for concrete and masonry facades

### DESCRIPTION

Sikaflex® Construction is a 1-component, moisture-curing, elastic joint sealant.

### USES

Sikaflex® Construction is designed for movement and connection joints on porous substrates as well as indoor and outdoor general sealing applications.

- Precast concrete construction
- Balcony parapets
- Bridge cantilevers
- Retaining walls
- Subways
- window frames and doors
- skirtings
- wall/floor joints
- shutter housings

### CHARACTERISTICS / ADVANTAGES

- Movement capability of  $\pm 25$  (ASTM C 719)
- Good workability
- Good adhesion to many substrates
- Can be overpainted
- Non-sag
- Bubble free curing formulation
- High tear resistance
- Weather resistance, excellent aging resistant

### APPROVALS / STANDARDS

- ISO 11600 F 20 LM
- ASTM C 920 class 25

### PRODUCT INFORMATION

|                           |  |
|---------------------------|--|
| <b>Chemical Base</b>      | Polyurethane   |
| <b>Packaging</b>          | 600 ml sausage, 20 sausages per box  |
| <b>Colour</b>             | White, Concrete Grey, Black, Beige, Dark Amber, Quartz Grey  |
| <b>Shelf Life</b>         | Sikaflex® Construction has a shelf life of 12 months from the date of production, if it is stored in undamaged, original, sealed packaging, and if the storage conditions are met. |
| <b>Storage Conditions</b> | Sikaflex® Construction shall be stored in dry conditions, where it is protected from direct sunlight.  |
| <b>Density</b>            | 1.35 kg/l approx. (ISO 1183-1)   |

### TECHNICAL INFORMATION

|                         |                                      |
|-------------------------|--------------------------------------|
| <b>Shore A Hardness</b> | 28 approx. (after 28 days) (ISO 868) |
|-------------------------|--------------------------------------|

|                                    |   |                            |
|------------------------------------|---|----------------------------|
| <b>Secant Tensile Modulus</b>      | 0.45 N/mm <sup>2</sup> approx. at 100% elongation (23 °C)<br>0.75 N/mm <sup>2</sup> approx. at 100% elongation (-20 °C) | (ISO 8339)                 |
| <b>Elongation at Break</b>         | 800% approx.  | (ISO 37)                   |
| <b>Elastic Recovery</b>            | 90% approx.   | (ISO 7389)                 |
| <b>Tear Propagation Resistance</b> | 6.0 N/mm approx.  | (ISO 34)                   |
| <b>Movement Capability</b>         | ± 25%<br>± 25%  | (ISO 9047)<br>(ASTM C 719) |
| <b>Service Temperature</b>         | -40 °C to +70 °C  |                            |

**Joint Design**  
The joint width must be designed to suit the joint movement required and the movement capability of the sealant. The joint width shall be ≥ 10 mm and ≤ 40 mm. A width to depth ratio of 2:1 must be maintained (for exceptions, see table below).

**Standard joint widths for joints between concrete elements**

| <b>Joint distance [m]</b> | <b>Min joint width [mm]</b> | <b>Min. joint depth [mm]</b> |
|---------------------------|-----------------------------|------------------------------|
| 2                         | 10                          | 10                           |
| 4                         | 15                          | 10                           |
| 6                         | 20                          | 10                           |
| 8                         | 30                          | 15                           |
| 10                        | 35                          | 17                           |

All joints must be correctly designed and dimensioned in accordance with the relevant standards, before their construction. The basis for calculation of the necessary joint widths are the type of structure and its dimensions, the technical values of the adjacent building materials and the joint sealing material, as well as the specific exposure of the building and the joints.

For larger joints please contact our Technical Service Department.

## APPLICATION INFORMATION

|                                |  |                         |                         |
|--------------------------------|--|-------------------------|-------------------------|
| <b>Consumption</b>             | <b>Joint length [m] per 600 ml sausage</b>             | <b>Joint width [mm]</b> | <b>Joint depth [mm]</b> |
|                                | 6  | 10                      | 10                      |
|                                | 4  | 15                      | 10                      |
|                                | 3  | 20                      | 10                      |
|                                | 2  | 25                      | 12                      |
|                                | 1.3  | 30                      | 15                      |
| <b>Backing Material</b>        | Use closed cell, polyethylene foam backing rods.       |                         |                         |
| <b>Sag Flow</b>                | 0 mm (20 mm profile, 50 °C)                            |                         | (ISO 7390)              |
| <b>Ambient Air Temperature</b> | +5 °C to +40 °C, min. 3 °C above dew point temperature |                         |                         |
| <b>Substrate Temperature</b>   | +5 °C to +40 °C  |                         |                         |
| <b>Curing rate</b>             | 3 mm/24 hours approx. (23 °C / 50% r.h.)               |                         | (CQP 049-2)             |
| <b>Skin Time</b>               | 90 minutes approx. (23 °C / 50% r.h.)                  |                         | (CQP 019-1)             |
| <b>Tooling Time</b>            | 80 minutes approx. (23 °C / 50% r.h.)                  |                         | (CQP 019-2)             |

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## LIMITATIONS

- Sikaflex® Construction can be over-painted with most conventional facade coating paint systems. However, paints must first be tested to ensure com-

patibility by carrying out preliminary trials (e.g. according to ISO technical paper: Paintability and Paint Compatibility of Sealants). The best over-painting results are obtained when the sealant is allowed to fully cure first. Note: non-flexible paint systems may impair the elasticity of the sealant and lead to cracking of the paint film

- Colour variations may occur due to exposure to chemicals, high temperatures and/or UV-radiation (especially with the colour shade white). However, a change in colour is purely of aesthetic nature and does not adversely influence the technical performance or durability of the product.
- Before use Sikaflex® Construction on natural stone contact our technical service department.
- Do not use Sikaflex® Construction on bituminous substrates, natural rubber, EPDM rubber or on any building materials which might bleed oils, plasticizers or solvents that could attack the sealant.
- Do not use Sikaflex® Construction to seal joints in and around swimming pools.
- Do not use Sikaflex® Construction for joints under water pressure or for permanent water immersion.
- Do not expose uncured Sikaflex® Construction to alcohol containing products as this may interfere with the curing reaction.

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet (MSDS) containing physical, ecological, toxicological and other safety-related data.

### VOC DATA

The maximum content of Sikaflex® Construction is 61 g/L VOC for the ready to use product.

## APPLICATION INSTRUCTIONS

### SUBSTRATE PREPARATION

The substrate must be clean, dry, sound and homogeneous, free from oils, grease, dust and loose or friable particles. Sikaflex® Construction adheres without primers and/or activators. However, for optimum adhesion and critical, high performance applications, such as on multi-story buildings, highly stressed joints, extreme weather exposure or water immersion, the following priming and/or pre-treatment procedures shall be followed:

#### Non-porous substrates

Aluminium, anodised aluminium, stainless steel, gal-

vanised steel, powder coated metals or glazed tiles have to be cleaned and pre-treated using Sika® Aktivator-100, wiped on and off with a clean towel. Before sealing, allow a drying time of > 15 minutes (< 2 hours).

Other metals, such as copper, brass and titanium-zinc, also have to be cleaned and pre-treated using Sika® Aktivator-100, wiped on and off with a clean towel. After the necessary flash-off time, use a brush to apply Sika® Primer-3 N and allow a further drying time of > 30 minutes (< 8 hours) before sealing the joints. PVC has to be cleaned and pre-treated using Sika® Primer-215 applied with a brush. Before sealing, allow a drying time of > 30 minutes (< 8 hours).

#### Porous substrates

Concrete, aerated concrete and cement based renders, mortars and bricks shall be primed using Sika® Primer-3 N applied with a brush. Before sealing, allow a flash-off time of > 30 minutes (< 8 hours).

For more detailed advice and instructions please contact the local Sika Technical Services Department.

Note: Primers are adhesion promoters. They are neither a substitute for the correct cleaning of a surface, nor do they improve the strength of the surface significantly.

### APPLICATION METHOD / TOOLS

Sikaflex® Construction is supplied ready to use. After the necessary substrate preparation, insert a suitable backing rod to the required depth and apply any primer if necessary. Insert a sausage into the sealant gun and extrude Sikaflex® Construction into the joint making sure that it comes into full contact with the sides of the joint and avoids any air entrapment. Sikaflex® Construction sealant must be firmly tooled against the joint sides to ensure adequate adhesion. It is recommended to use masking tape where exact joint lines or neat lines are required. Remove the tape within the skin time. Use a compatible tooling agent to smooth the joint surfaces. Do not use tooling products containing solvents.

If Sikaflex® Construction is dry-tooled it shows a slightly structured, concrete-like surface. If it is wet-tooled (using a compatible tooling agent) it shows a smooth surface.

### CLEANING OF TOOLS

Clean all tools and application equipment immediately after use with Sika® Remover-208. Once cured, residual material can only be removed mechanically.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

### SIKA HONGKONG LTD.

Rm.1507-12, Blk A, New Trade Plaza,  
6 On Ping Street, Shatin, N.T., H.K.  
Phone: +852 26868108  
Fax: +852 26453671  
Mail: [marketing@hk.sika.com](mailto:marketing@hk.sika.com)  
Website: [www.sika.com.hk](http://www.sika.com.hk)



**Product Data Sheet**  
Sikaflex® Construction  
January 2021, Version 01.02  
02051101000000019

SikaflexConstruction-en-HK-(01-2021)-1-2.pdf