

PRODUCT DATA SHEET

SikaWrap®-430 G

WOVEN UNIDIRECTIONAL GLASS FIBRE FABRIC, DESIGNED FOR STRUCTURAL STRENGTHENING APPLICATIONS AS PART OF THE SIKA® STRENGTHENING SYSTEM.

DESCRIPTION

SikaWrap®-430 G is a unidirectional woven glass fibre fabric designed for installation using the dry or wet application process.

USES

SikaWrap®-430 G may only be used by experienced professionals.

Structural strengthening of reinforced concrete, masonry, brickwork and timber elements or structures, to increase flexural and shear loading capacity for:

- Improved seismic performance of masonry walls
- Increasing the strength and ductility of columns
- Enabling changes in use / alterations and refurbishment
- Correcting structural design and / or construction defects
- Increasing resistance to seismic movement
- Improving service life and durability
- Structural upgrading to comply with current standards
- Blast mitigation (accidents or terrorism)
- Electrical environments that ask for non-conductive material

CHARACTERISTICS / ADVANTAGES

- Manufactured with heat-set weft fibres to keep the fabric stable
- Multifunctional fabric for use in many different strengthening applications
- Flexible and accommodating to different surface planes and geometry (beams, columns, chimneys, piles, walls, soffits, silos etc.)
- Low density for minimal additional weight
- Cost effective in comparison to traditional strengthening techniques
- Very low electrical conductivity

PRODUCT INFORMATION

Construction	Fibre orientation	0° (unidirectional)	
	Warp	White glass fibres 98 %	
	Weft	White thermoplastic heat-set fibres 2 %	
Fibre Type	E-glass fibres		
Packaging		Fabric length per roll	Fabric width
	1 roll in cardboard box	≥ 50 m	600 mm
Shelf Life	24 months from date of production		

Storage Conditions	Store in undamaged, original sealed packaging and in dry conditions. Protect from direct sunlight.		
Dry Fibre Density	2.56 g/cm ³		
Dry Fibre Thickness	0.168 mm (based on total glass content)		
Density	430 g/m ² + 10 g/m ² (glass fibres only)		
Dry Fibre Tensile Strength	2 500 N/mm ² (measured on roving)		(EN 2561)
Dry Fibre Modulus of Elasticity in Tension	72 000 N/mm ²		(EN 2561)
Dry Fibre Elongation at Break	2.7 % (measured on roving)		(EN 2561)

TECHNICAL INFORMATION

Laminate Nominal Thickness	0.168 mm		
Laminate Nominal Cross Section	168 mm ² per m width		
Laminate Tensile Strength	Average 1 500 N/mm ²	Characteristic 1 200 N/mm ²	(EN 2561*) (ASTM 3039*)
Laminate Modulus of Elasticity in Tension	Average 70 kN/mm ²	Characteristic 68 kN/mm ²	(EN 2561*) (ASTM 3039*)
	* modification: sample with 50 mm Values in the longitudinal direction of the fibres Single layer, minimum 27 samples per test series		
Laminate Elongation at Break in Tension	2.14 %		(based on EN 2561) (based on ASTM 3039)
Tensile Resistance	Average 252 kN/m	Characteristic 202 kN/m	(based on EN 2561) (based on ASTM 3039)
Tensile Stiffness	Average 11.8 MN/m 11.8 kN/m per % elongation	Characteristic 11.4 MN/m 11.4 kN/m per % elongation	(based on EN 2661) (based on ASTM 3039)

SYSTEM INFORMATION

System Structure	The system build-up and configuration as described must be fully complied with and may not be changed.
	Concrete substrate adhesive primer Sikadur®-330
	Impregnating / laminating resin Sikadur®-330 or Sikadur®-300
	Structural strengthening fabric SikaWrap®-430 G
	For detailed information on Sikadur®-330 or Sikadur®-300, together with the resin and fabric application details, please refer to the Sikadur®-330 or Sikadur®-300 Product Data Sheet and the relevant Method Statement.

APPLICATION INFORMATION

Consumption	Dry application with Sikadur®-330
	First layer including primer layer 1.2–1.6 kg/m ²
	Following layers 1.0 kg/m ²
	Wet application with Sikadur®-300, primer Sikadur®-330
	Primer layer 0.5–0.7 kg/m ²
	Fabric layers 0.7 kg/m ²
	Please also refer to the relevant Method Statement for further information.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

Minimum substrate tensile strength: 1.0 N/mm² or as specified in the strengthening design.
Please also refer to the relevant Method Statement for further information.

SUBSTRATE PREPARATION

Concrete must be cleaned and prepared to achieve a laitance and contaminant free, open textured surface.
Please also refer to the relevant Method Statement for further information.

APPLICATION METHOD / TOOLS

The fabric can be cut with special scissors or a Stanley knife (razor knife / box-cutter knife). Never fold the fabric.

SikaWrap®-430 G is applied using the dry or wet application process.
Please refer to the relevant Method Statement for details on the impregnating / laminating procedure.

LIMITATIONS

- SikaWrap®-430 G shall only be applied by trained and experienced professionals.
- A specialist structural engineer must be consulted for any structural strengthening design calculation.
- SikaWrap®-430 G fabric is coated to ensure maximum bond and durability with the Sikadur® adhesives / impregnating / laminating resins. To maintain and ensure full system compatibility, do not interchange different system components.
- SikaWrap®-430 G can be over coated with a cementitious overlay or other coatings for aesthetic and / or protective purposes. The over coating system selection is dependent on the exposure and the project specific requirements. For additional UV light protection in exposed areas use Sikagard®-550 W Elastic, Sikagard® ElastoColor-675 W or Sikagard®-680 S.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

SIKA HONGKONG LTD.

Rm.1507-12, 15/F, Block A,
New Trade Plaza,
6 On Ping Street,
Shatin, N.T.
Hong Kong.



Product Data Sheet
SikaWrap®-430 G
July 2019, Version 02.01
020206020020000001

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

ECOLOGY, HEALTH AND SAFETY

REGULATION (EC) NO 1907/2006 - REACH

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in the product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0,1 % (w/w)

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

SikaWrap-430G-en-HK-(07-2019)-2-1.pdf