

SYSTEM DATA SHEET

Sikafloor® MultiDur EB-24

Broadcast unicolour epoxy floor covering with high mechanical resistance

DESCRIPTION

Sikafloor® MultiDur EB-24 is a slip resistant, coloured, epoxy covering with high mechanical resistance for flooring applications

USES

Sikafloor® MultiDur EB-24 may only be used by experienced professionals.

- for concrete and cement screeds with normal up to medium heavy wear e.g. storage and assembly halls, maintenance workshops, garages and loading ramps.
- for multi-storey and underground car parks and for wet process areas, e.g. beverage and food industry

CHARACTERISTICS / ADVANTAGES


- High wear resistance
- High mechanical resistance
- Good chemical resistance
- Easy application
- Waterproof
- Gloss finish
- Slip resistant

APPROVALS / STANDARDS

- Fire classification test, Bfl-S1 according to DIN EN 13501-1, Report No.2007-B-0181/15, Germany, July 2007

SYSTEM INFORMATION

System Structure



Sikafloor® MultiDur EB-24 system (~ 2–4 mm)

1. Primer	Sikafloor®-156/-161/-160
2. Wearing coat & broadcast in excess	Sikafloor®-263 SL or Sikafloor®-264 broadcast with quartz sand in excess
3. Top coat	Sikafloor®-264 or Sikafloor®-263 SL

SYSTEM DATA SHEET

Sikafloor® MultiDur EB-24
January 2024, Version 04.03
02081190000000017

Composition	Epoxy
Appearance	Slip resistant, gloss finish
Colour	Available in various colour shades.
Nominal thickness	~2.0–4.0 mm

TECHNICAL INFORMATION

Reaction to Fire	Bfl-S1	(DIN EN 13501-1)
Chemical Resistance	Refer to the chemical resistance of Sikafloor®-264 or Sikafloor®-263 SL	
Thermal Resistance	Exposure*	Dry heat
	Permanent	+50 °C
	Short-term max. 7 d	+80 °C
	Short-term max. 12 h	+100 °C
	Short-term moist/wet heat* up to +80 °C where exposure is only occasional (i.e. during steam cleaning etc.)	
	*No simultaneous chemical and mechanical exposure.	
Skid / Slip Resistance	R11 V4 (Quartz Sand 0.3-0.8 mm)	(DIN 51130)
	R12 V6 (Quartz Sand 0.7-1.2 mm)	(DIN 51130)

APPLICATION INFORMATION

Consumption	Sikafloor® MultiDur EB-24 system (~ 2–4mm)		
	Coating System	Product	Consumption
	Primer	1 x Sikafloor®-156 /-160/-161	~ 0.3–0.5 kg/m ²
	Wearing coat	Sikafloor®-263 SL or Sikafloor®-264 filled 1:1 with quartz sand 0.1–0.3mm	~ 4 kg /m ² (2 kg/m ² binder + 2 kg/m ² quartz sand)
	Broadcast in excess	quartz sand 0.4 – 0.7 mm	~ 4–6 kg/m ²
	Top coat	1–2 x Sikafloor®-264 or Sikafloor®-263 SL	~0.6–0.8 kg/m ²
Product Temperature	Please refer to the individual Product Data Sheet		
Ambient Air Temperature	+10 °C min. / +30 °C max.		
Relative Air Humidity	80 % r.h. max.		
Dew Point	Beware of condensation! The substrate and uncured floor must be at least 3 °C above dew point to reduce the risk of condensation or blooming on the floor finish.		
Substrate Temperature	+10 °C min. / +30 °C max.		
Substrate Moisture Content	When performing application work with Sikafloor® MultiDur EB-24, the substrate moisture content must not exceed 4 % pbw measured by Tramex. Test method: Sika®-Tramex meter, CM - measurement or Oven-dry-method. No rising moisture according to ASTM (Polyethylene-sheet).		

Waiting Time / Overcoating

Before applying Sikafloor®-263 SL/-264 on Sikafloor®-156/161/160 allow:

Substrate temperature	Minimum	Maximum
+10 °C	24 hours	3 days
+20 °C	12 hours	2 days
+30 °C	8 hours	1 day

Before applying Sikafloor®-264 on Sikafloor®-263 SL/-264 allow:

Substrate temperature	Minimum	Maximum
+10 °C	30 hours	48 hours
+20 °C	24 hours	24 hours
+30 °C	16 hours	30 hours

Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity

Applied Product Ready for Use

Temperature	Foot traffic	Light traffic	Full cure
+10 °C	~ 72 hours	~ 6 days	~ 10 days
+20 °C	~ 24 hours	~ 4 days	~ 7 days
+30 °C	~ 18 hours	~ 2 days	~ 5 days

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER DOCUMENTS

Please refer to :

- Sika® Method Statement Mixing & Applications of Flooring systems
- Sika® Method Statement Evaluation and Preparation of Surfaces for Flooring systems

LIMITATIONS

- Do not apply Sikafloor® MultiDur EB-24 on substrates with rising moisture.
- Freshly applied Sikafloor® MultiDur EB-24 must be protected from damp, condensation and water for at least 24 hours.
- The incorrect assessment and treatment of cracks may lead to a reduced service life and reflective cracking.
- For exact colour matching, ensure the Sikafloor®-264 in each area is applied from the same control batch numbers.
- Under certain conditions, underfloor heating or high ambient temperatures combined with high point loading, may lead to imprints in the resin.
- If heating is required do not use gas, oil, paraffin or other fossil fuel heaters, these produce large quantities of both CO₂ and H₂O water vapour, which may adversely affect the finish. For heating use only electric powered warm air blower systems.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet (MSDS) containing physical, ecological, toxicological and other safety-related data.

MAINTENANCE

CLEANING

Please refer to the Method Statement Sikafloor®-Cleaning Regime

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

SYSTEM DATA SHEET

Sikafloor® MultiDur EB-24
January 2024, Version 04.03
02081190000000017

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

SIKA HONGKONG LTD.

Rm.1507-12, Blk A, New Trade Plaza,
6 On Ping Street, Shatin, N.T., H.K.
Phone: +852 26868108
Fax: +852 26453671
Mail: marketing@hk.sika.com
Website: www.sika.com.hk



SYSTEM DATA SHEET

Sikafloor® MultiDur EB-24
January 2024, Version 04.03
020811900000000017

SikafloorMultiDurEB-24-en-HK-(01-2024)-4-3.pdf