

PRODUCT DATA SHEET

SikaTop®-107 Seal HK

Polymer-modified Cementitious Waterproofing Slurry and Protective Coating

**DESCRIPTION**

SikaTop®-107 Seal HK is a two part polymer modified cementitious waterproof slurry composed of a liquid polymer and a cement based mix incorporating special admixtures. It is applied to concrete and mortar to prevent water infiltration.

USES

- Interior waterproofing and damp-proofing of concrete, cementitious rendering, brickwork and block-work
- Pore / blowhole filling
- Sealing fine “hairline” cracks in concrete structures (not subject to movement)
- Protection against water ingress

Areas of application

- Concrete water tanks / reservoirs
- Terraces and balconies(not exposed to direct sunlight type)
- Retaining walls
- Bathroom / toilets
- Tile grouting in water tanks

CHARACTERISTICS / ADVANTAGES

- Easy to apply by brush or in thin trowel applications
- Prebagged components with consistence quality
- Hand or spray applied
- Very good adhesion
- Protects against water penetration
- Non toxic
- Non-corrosive to steel or iron
- Overpaintable

PRODUCT INFORMATION

Chemical Base	Part A : liquid polymer and additive Part B : portland cement, selected aggregate and admixtures
Packaging	25 kg set (20 kg bag and 5 kg pail)
Appearance / Colour	Part A : white liquid Part B : grey or white powder Mixed product : cement grey or off-white
Shelf Life	9 months from date of production
Storage Conditions	If stored properly in undamaged and unopened original sealed packaging in cool dry conditions. Protect from direct sunlight and frost.
Density	Approx. 1.9–2 kg/L (Freshly mixed mortar)

TECHNICAL INFORMATION

Compressive Strength	~ 32 MPa	(ASTM C109-05)
Tensile Strength in Flexure	~ 10 MPa	(ASTM C348-95)
Tensile Strength	~ 2.5 MPa	(ASTM D412-16)
Tensile Adhesion Strength	~ 1 MPa	(ASTM D4541-09)

APPLICATION INFORMATION

Mixing Ratio	Used as slurry : A : B = 1 : 4 (by weight) Used as mortar : A : B = 1 : 4.5 (by weight)	
Consumption	Dependent on the application area, substrate roughness, surface profile and thickness, consumption for one coat is : <ul style="list-style-type: none">▪ Waterproofing for bathrooms, terraces and balconies, etc. ~ 1.0 kg/m²/coat▪ Waterproofing coating for crucial areas ~ 2.0 kg/m²/coat Note: <ul style="list-style-type: none">▪ SikaTop®-107 Seal HK must be applied in minimum 2 coats.▪ 3 coats may be required in areas of extremely high infiltration.▪ Ronacrete Unicell® WF with primer as protective render is recommended.	
Ambient Air Temperature	+8 °C min. / +35 °C max.	
Substrate Temperature	+8 °C min. / +35 °C max.	
Pot Life	~ 30 minutes at +30 °C (Pot life will be shortened at higher temperatures.)	
Waiting Time / Overcoating	<i>Waiting time between coats:</i>	
	+10 °C	~ 12 hours
	+20 °C	~ 6 hours
	+30 °C	~ 3 hours
If waiting time period exceeds 24 hours, lightly clean up the surface. For overcoating with cementitious materials, please ensure SikaTop®-107 Seal HK is hardened and strong enough to hold the topping materials. For use in water-retaining structures or for applying renders over it or for overcoating with non-cementitious materials, please consult our Technical Services Department.		

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LIMITATIONS

SikaTop®-107 Seal HK is not a decorative treatment and may display signs of “blooming” after rain or in damp weather. This does not affect the performance of the coating, in any way. Where SikaTop®-107 Seal HK will be visible after completion of the works, then the off-white colour, which is aesthetically more pleasing should be used. Where a decorative finish is required, overpaint SikaTop®-107 Seal HK with approved protective and decorative coating is recommended.

Avoid application in direct sun and / or strong wind. Do not add water in any circumstances. Apply only to sound, prepared substrates and surfaces should be well dampened but free of surface water and leaks.

Protect freshly applied material from direct rain for at least 4 hours.

SikaTop®-107 Seal HK does not provide a trafficable finish, it should cover with protective screed where necessary.

SikaTop®-107 Seal HK will not bond well to surfaces that have been treated previously with water repellent.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

VOC DATA

VOC content (ready to use) not exceeding 10 gm/litre [Type of regulated paint under the Air Pollution Control (volatile organic compounds) Regulation of Hong Kong: (waterproofing sealer)].

APPLICATION INSTRUCTIONS

EQUIPMENT

SikaTop®-107 Seal HK must be mechanically mixed using a forced action mixer or in a clean drum using a drill and paddle (max. 500 rpm). A normal concrete free fall mixer is NOT suitable.

SUBSTRATE QUALITY / PRE-TREATMENT

SURFACE QUALITY

The substrate must be structurally sound and free of all traces of contaminants, loose and friable particles, cement laitance, sharp edges, oils and grease, etc. The concrete "pull off" (tensile adhesive) strength must be $> 1 \text{ N/mm}^2$.

SURFACE PREPARATION

General:

The substrate must be prepared by suitable mechanical preparation techniques such as high pressure water jetting, needle guns, blastcleaning, scabblers, etc. and properly pre-wetted to a saturated surface dry condition.

For pore / blowhole filling:

Blast clean to remove all contaminants including from within the pores / blowholes.

As a levelling mortar:

Prepare and clean all surfaces by suitable mechanical means such as abrasive blast cleaning or equivalent to ensure cement laitance, surface contamination and all existing coatings are removed and all blowholes and honeycombed areas are exposed. The resultant surface must be profiled to achieve maximum bond strength.

Absorbent surfaces have to be thoroughly saturated with water prior to application of first coat of SikaTop®-107 Seal HK. However no standing water should be on the surface before application.

All intersections of horizontal and vertical surfaces should be profiled with a mortar fillet of 25 mm × 25 mm

MIXING

Shake part A before using it. Pour approximately half of part A into the mixing container and add part B slowly while mixing. Add the remainder of part A and continue mixing until a uniform lump free consistency is achieved. Mixing time ~ 3 minutes.

MIXING TOOLS

SikaTop®-107 Seal HK must be mechanically mixed using a forced action mixer or in a clean drum using a drill and paddle (max. 500 rpm). A normal concrete free fall mixer is NOT suitable.

APPLICATION

The surface must be pre-wetted to a saturated surface dry condition with no standing water at time of application.

As a slurry:

Apply the mixed SikaTop®-107 Seal HK by hand or spray using a stiff brush or roller or broom in the same direction. Apply the second coat of SikaTop®-107 Seal HK in crosswise direction to the first application as soon as first coat has hardened.

As a mortar:

When SikaTop®-107 Seal HK is applied by trowel (e.g. for a smooth surface finish), the product must be mixed with a 10 % reduction of part A (A : B = 1 : 4.5). Apply the second coat of SikaTop®-107 Seal HK as soon as the first coat has hardened. For pore / blowhole filling, tightly trowel into the pores /

blowholes of the surface.

For floor applications, it is recommended to apply the second coat within 24 hours to avoid damage to the first coat. If the second coat is applied 12 hours or later, the first coat shall be slightly prewetted, preferably by using a fine spray. A better finish can be achieved by rubbing down with a soft, dry sponge after applying the second coat.

Sika® SealTape F is a recommended product to be used in conjunction with SikaTop®-107 Seal HK in order to achieve advanced water tightness in wet rooms and around wet area.

For more details, please contact our Technical Services Department.

CURING TREATMENT

For cement based products, proper curing is important. Protect newly applied SikaTop®-107 Seal HK against direct sunlight, wind, rain and frost to ensure full cement hydration and minimise cracking.

CLEANING OF TOOLS

Clean all tools and application equipment with clean water immediately after use. Hardened / cured material can only be removed mechanically.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

SIKA HONGKONG LTD.

Rm.1507-12, Blk A, New Trade Plaza,
6 On Ping Street, Shatin, N.T., H.K.
Phone: +852 26868108
Fax: +852 26453671
Mail: marketing@hk.sika.com
Website: www.sika.com.hk



Product Data Sheet

SikaTop®-107 Seal HK
April 2025, Version 06.04
020701010020000127

SikaTop-107SealHK-en-HK-(04-2025)-6-4.pdf