

#### **BUILDING TRUST**

# PRODUCT DATA SHEET

# Sikagard®-405 W

Single component, waterborne, modified acrylic coating

#### **DESCRIPTION**

Sikagard®-405 W is a single component white, waterborne acrylic resin based coating containing an organic in-fim-preservative with a mid-sheen finish

## **USES**

Sikagard®-405 W may only be used by experienced professionals.

- Top coat or stand alone coating for internal walls and ceilings
- For concrete, bricks, cement based and gypsum substrates, metallic surfaces, timber, tiles and plastic
- Suitable for pharmaceutical, medical engineering, food & Beverage industry, hospitals, healthcare facilities, prisons and leisure facilities

## **CHARACTERISTICS / ADVANTAGES**

- Good resistance to repeated cleaning and disinfection regimes, using mild detergents and cleaning solutions
- Tough and highly durable
- Good covering and hiding power (opacitiy)
- Permeable to water vapour
- Ultra low emission
- Odourless
- Seemless, easy to clean finish
- Easy to apply
- Mid-sheen finish

## **ENVIRONMENTAL INFORMATION**

- Sikagard®-405 W conforms to the requirements of LEED EQ Credit 4.2: Low emitting Materials: Paints & Coatings, SCAQMD Method 304-9; VOC Content <100g/l</li>
- Sikagard®-405 W is listed on the Eco-Product Directory as environmental friendly product choice for green building initiatives (application no.: PL-01605-2023)

### **APPROVALS / STANDARDS**

- Eurofins, test report No. 392-2016-00071401\_E\_EN, VOC emission acc. French Regulations Decret DEVL 11019093D and Decret DEVL 11034675A, October 20th 2015
- Exova Warringtonfire, test report No. 363979, behaviour to fire acc. BS 476, April 27th 2016
- Eurofins, test report No. 392-2015-00386901, determination of VOC and SVOC content acc.
   ISO 11890-2, CEPE/EC/2015-04-13 and the Commission Decision 2014/312/EU, December 10th 2015
- PRA, test report No. 77584-049, gloss, fineness, grind wet scrub resistance and contrast ratio acc. EN 13300, January 29th 2016
- IMSL, test report No. 2015/02/004.1A, determination of antibacterial activity acc. ISO 22196, May 12th 2015
- Campden BRI Group, test report No. S/REP/138532/1, Sensory Evaluation of the Taint Potential, Triangle Test Method TES-S-002, Odour Transfer Meethod, March 2nd 2016
- 4wardtesting, test report No. C2905, water vapour transmission rate and water vapour pemeability acc. ISO 7783-1:2000, January 5th 2016

## PRODUCT INFORMATION

Chemical Base	Waterborne, acrylic copolymer dispersion		
Packaging	5.0 litres = 6.60 kg drums 15.0 litres = 19.80 kg drums		
Shelf Life	12 month from date of production		
Storage Conditions	The product must be stored in original, unopened and undamaged sealed packaging in dry and cool conditions protect from direct sunlight and frost. Always refer to packaging.		
Appearance / Colour	white		
Density	~1.31 kg/l	(EN ISO 2811-1)	
Solid Content by Weight	~42%		
Solid Content by Volume	~55%		

## **TECHNICAL INFORMATION**

Tensile Strength	~10 N/mm²	(EN ISO 527-3)	
Elongation at Break	~70%		
Tensile Adhesion Strength	≥ 1.5N/mm² to concrete with Sika Bonding Primer	(ISO 4624)	
Permeability to Water Vapour	~51.5 g/m² in 24 hours	(EN ISO 7783-1:2011)	
Chemical Resistance	Good short term resistance to mild acids, alkalis, cleaning agents and disin-		

Good short term resistance to mild acids, alkalis, cleaning agents and disinfectants. Please contact local Sika Technical service for specific informa-

Disinfection with Hydrogen Peroxide Vapor:

- Resistant when using STERIS VHP technology
- Resistant to PEA vaporisation technology according Test report PEA
- Resistant when using Oxypharm vaporiser NOCOSPRAY with the following set-up:

Disinfectant	Concentration	Setting at vaporiser	Contact time
NOCOLYSE Mint (6%)	1 ml/m³	20m³ (1.5 min vapor-	30 min
(070)		isation)	
NOCOLYSE ONE Shot	3 ml/m³	45m³ (5	30 min
(12%)	(2cycles)	minutes va-	
		porisation)	
NOCOLYSE Food	1 ml/m³	20m³ (1.5	30 min
(7.9%)		minutes va-	
		porisation	
NOCOLYSE Food	5 ml/m³	75m³ (5	60 min
(7.9%)		minutes va-	
		porisation)	

## **APPLICATION INFORMATION**

Consumption	~0.20 kg/m² per layer ~0.15 l/m² per layer
Layer Thickness	~120μm
Ambient Air Temperature	+8°C - +35°C
Relative Air Humidity	80% max.

**Product Data Sheet** Sikagard®-405 W May 2023, Version 02.02 020813020020000023



Dew Point	3 °C above dew point Beware of condensation	1	
Substrate Temperature	+8°C - +35°C		
Curing Time	Before applying Sikagard®-405 W to Sikagard®-405 W allow:		
	Substrate Temperature	Minimum	Maximum
	+10°C	4 hours	7 days
	+20°C	2 hours	7 days
	+30°C	1 hour	7 days
	Before applying Sikagard®-405 W to Sikagard®-403 W allow:		
	<b>Substrate Temperature</b>	Minimum	Maximum
	+10°C	4 hours	7 days
	+20°C	1 hours	7 days
	+30°C	1 hour	7 days
Applied Product Ready for Use	Temperature	Tack free	Full cure
	+10°C	8 hours	7 days
	+20°C	4 hours	7 days
	+30°C	3 hours	7 days

#### **BASIS OF PRODUCT DATA**

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

#### **LIMITATIONS**

- Each method of application will leave a different surface finish. If it is important do not mix methods within single areas.
- Each rype of roller will give a slightly different surface finish always use same roller type in same areas
- Ensure entire surface is fully dried before proceeding. Crazing may occur when over coating undried surfaces or when applying excessively thick material.
- Do not apply over silicone sealants
- The gloss of applied material is influenced by humidity, temperature and absorbency of the substrate
- Always ensure good ventilation when application takes place in a confined space, to ensure drying and full curing
- The incorrect assessment and treatment of cracks may lead to a reduced service life and reflective cracking.
- For spray application the use of personal health and safety equipment is mandatory
- If heating is required do not use gas oil, paraffin or other fossil fuel heaters, these produce CO₂ and water vapour, which may adversely affect the finish. For heating use only electric powered warm air blower systems
- New concrete should be allowed to cure/ hydrate for a minimum of 10 days and preferably 28 days
- Do not apply near food stuff in unventilated conditions, always ensure adequate ventilation
- Do not thin or brush out like conventional paints
- Acoustic boards may lose some acoustic absorption after coating

## **ECOLOGY, HEALTH AND SAFETY**

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet (MSDS) containing physical, ecological, toxicological and other safety-related data.

#### **VOC DATA**

According to the EU Directive 2004/42/CE, the maximum allowed content of VOC (product category IIA / i type wb) is 140 g/l (Limits 2010) for the ready to use product.

The maximum content of Sikagard®-405 W is  $\leq$  140 g/l VOC for the ready to use product.



#### APPLICATION INSTRUCTIONS

#### APPLICATION

Stir product mechanically until a uniform liquid has been achieved. Use low speed electrical stirrer (300-400rpm) tp avoid air entrapment.

For roller application use short piled roller. For airless application use tip size 0.38 to 0.53mm/ Angle 40° to 60°.

#### **CLEANING OF TOOLS**

Clean all tools and application equipment woth water immediately after use. Hardened and/ or cured material can only be removed mechanically or with proprietary paint stripper.

## **LOCAL RESTRICTIONS**

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

#### **LEGAL NOTES**

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

## SIKA HONGKONG LTD.

Rm.1507-12, Blk A, New Trade Plaza, 6 On Ping Street, Shatin, N.T., H.K. Phone: +852 26868108 Fax: +852 26453671 Mail: marketing@hk.sika.com Website: www.sika.com.hk





**Product Data Sheet Sikagard®-405 W**May 2023, Version 02.02
020813020020000023



Sikagard-405W-en-HK-(05-2023)-2-2.pdf