

PRODUCT DATA SHEET

Sikafloor®-81 EpoCem® ID

3-PART CEMENT AND EPOXY COMBINATION MORTAR FOR MOISTURE BARRIER AND SELF-SMOOTHING FLOOR SCREEDS OF 1.5 TO 3 MM

DESCRIPTION

Sikafloor®-81 EpoCem® ID is a three part, epoxy modified cementitious, fine textured mortar for moisture barrier and self smoothing floor screeds in thin layers of 1.5 to 3 mm.

USES

Sikafloor®-81 EpoCem® ID may only be used by experienced professionals.

As a Temporary Moisture Barrier (TMB) (min. 2 mm thick) allowing the application of Epoxy, Polyurethane and PMMA* resin floors requiring dry substrates, over high moisture content substrates, even green concrete, for a lasting solution.

As a self-smoothing screed for:

- Levelling or patching horizontal concrete surfaces, in new work or repairs, in aggressive chemical environments
- Floor topping on non-ventilated damp substrates without particular aesthetic requirements
- Levelling layer under Epoxy, Polyurethane and PMMA* floor coatings / screeds, tiles, sheet floors, carpets or wooden floors
- Repair and maintenance of monolithic and vacuum concrete floors

Extended with quartz sand, as a patching and repair mortar:

- Under Epoxy, Polyurethane and PMMA floor coatings/screeds

CHARACTERISTICS / ADVANTAGES

- Can be overcoated with epoxy resin compounds after 24 hours (+20 °C, 75 % r.h.)
- Prevents osmotic blistering of resin based coatings over damp substrates
- Economical and fast, easy application
- Good levelling properties
- Impervious to liquids but permeable to water vapour
- Frost and de-icing salt resistant
- Thermal expansion properties similar to concrete
- Excellent bond to green or hardened concrete whether damp or dry
- Excellent early and final mechanical strengths
- Excellent resistance to water and oils
- Ideal preparation for smooth surface finishes
- For internal use
- Contains no solvents
- Will not corrode reinforcement

PRODUCT INFORMATION

Chemical Base	Epoxy modified cementitious mortar
Packaging	Pre-batched 23 kg units Sikafloor® EpoCem® Modul Comp.A 1.14 kg plastic container Sikafloor® EpoCem® Modul Comp.B 2.86 kg plastic container Sikafloor®-81 EpoCem® ID Comp.C 19.00 kg bag
Shelf Life	Sikafloor® EpoCem® Modul Comp.A 12 months & Comp.B : Sikafloor®-81 EpoCem® ID Comp.C : 9 months

From date of production if stored in original, unopened and undamaged sealed packaging.

Storage Conditions	The product must be stored in original, unopened and undamaged sealed packaging, in dry conditions at temperatures between +5 °C and +30 °C.		
	Sikafloor® EpoCem® Modul Comp.A & Comp.B :	Protect from frost and direct sunlight	
	Sikafloor®-81 EpoCem® ID Comp.C :	Protect from humidity and direct sunlight	
Appearance / Colour	Sikafloor® EpoCem® Modul Comp.A White liquid - resin: Sikafloor® EpoCem® Modul Comp.B Translucent yellow liquid - hardener: Sikafloor®-81 EpoCem® ID Comp.C - Natural grey aggregate powder filler: Colour: Light grey Finish Colour: Matt grey		
Density	Sikafloor® EpoCem® Modul Comp.A :	~1.09 kg/L	(EN 1015-6) at +20 °C
	Sikafloor® EpoCem® Modul Comp.B :	~1.03 kg/L	
	Sikafloor®-81 EpoCem® ID Comp.C :	~1.72 kg/L	
	Sikafloor®-81 EpoCem® ID:	~2.10 kg/L	

TECHNICAL INFORMATION

Compressive Strength	1 day	~15 N/mm ²	(EN 13892-2)
	7 days	~38 N/mm ²	
	28 days	~44 N/mm ²	

Tensile Strength in Flexure	28 days	~10 N/mm ²	(EN 13892-2)
------------------------------------	---------	-----------------------	--------------

Chemical Resistance	The Sikafloor® EpoCem® product range has improved chemical resistance over plain concrete in aggressive environments, but is not designed as a chemical protection. For specific chemical resistance, always overcoat with a suitable product from the Sikafloor® and Sikagard® range. For occasional exposure or spillages, consult technical department.		
----------------------------	--	--	--

SYSTEM INFORMATION

Systems	<p>The system configuration as described must be fully complied with and may not be changed.</p> <p>Primer indicated below is suitable for each of these substrates:</p> <ul style="list-style-type: none">▪ Green concrete (as soon as mechanical preparation is possible)▪ Damp concrete (> 14 days old)▪ Damp aged concrete (rising moisture) <p>Patching and repair: Layer thickness: 3 – 9 mm Primer: SikaTop®-Armotec®-110 EpoCem® Mortar: Sikafloor®-81 EpoCem® ID -Extended mortar mix. (See mixing for details)</p> <p>Levelling screed for medium substrate roughness: Layer thickness: 1.5 - 3 mm Primer: Sikafloor® EpoCem® Modul Screed: Sikafloor®-81 EpoCem® ID</p> <p>Top coat: Suitable product from the Sikafloor® and Sikagard® range. Interlayer priming for Sikafloor®-81 EpoCem® ID Bonding bridge: Sikafloor® EpoCem® Modul</p>		
----------------	---	--	--

APPLICATION INFORMATION

Mixing Ratio	Comp.A : Comp.B : Comp.C - packing size : 1.14 : 2.86 : 19 kg	
	Flooring Screed:	
	At temperatures between +12 °C to +25 °C:	
	1 : 2.5 : 17 (by weight)	
	Comp. (A+B) : C = 4 kg : 19 kg	
	At temperatures between +8 °C to +12 °C and +25 °C to +30 °C:	
	The amount of Comp.C can be reduced to 18 kg in order to improve workability.	
	Please note:	
	Never reduce Comp.C by more than this amount.	
	1 : 2.5 : 15.8 (by weight)	
Comp. (A+B) : C = 4 kg : 18 kg		
Consumption	Extended mortar mix. Repair mortar:	
	To repair surface irregularities and holes 3 to 5 cm in diameter and deeper than 3 mm and up to 9 mm the standard Sikafloor®-81 EpoCem® ID mix can be extended with dry quartz sand.	
	For each 23 kg unit of Sikafloor®-81 EpoCem® ID prepared as indicated below, add:	
	▪ Quartz sand 0.7 - 1.2 mm, 5 - 10 kg	
	▪ Quartz sand 2.0 - 3.0 mm, 5 - 10 kg	
	Final mix will be : 33 - 43 kg	
	For this application, to achieve a good bond of the mortar to the substrate, SikaTop®-Armatec®-110 EpoCem® must be used as bonding bridge. Apply the mortar wet on wet to the primer.	
	Primer:	Sikafloor® EpoCem® Modul ~0.3 kg/m ²
	Self smoothing screed:	Sikafloor®-81 EpoCem® ID ~2.25 kg/m ² /mm
	These figures are theoretical and do not allow for any additional material due to surface porosity, surface profile, variations in level or wastage, etc.	
Layer Thickness	1.5 mm min. / 3.0 mm max. If Sikafloor®-81 EpoCem® ID is used as a Temporary Moisture Barrier (TMB), a minimum of 2 mm must be applied.	
Ambient Air Temperature	+10 °C min. / +30 °C max.	
Relative Air Humidity	20 % min. / 80 % max.	
Substrate Temperature	+10 °C min. / +30 °C max.	
Substrate Moisture Content	Can be applied on green or damp concrete, without any standing water. Although the product can be applied onto green concrete surfaces (> 24 hours), it is advised to allow at least 3 days for early shrinkage of concrete to occur in order to prevent concrete shrinkage cracks from appearing on the screed surface.	
Pot Life	Temperature / R.H 75%	Time
	+10 °C	~40 min
	+20 °C	~20 min
	+30 °C	~15 min
	23 kg units	

Curing Time

Once Sikafloor®-81 EpoCem® ID is tack free it is possible to apply vapour permeable seal coats.

For the application of vapour tight coatings on Sikafloor®-81 EpoCem® ID, allow the surface moisture to fall below 4 %, not earlier than:

Substrate Temperature	Waiting Time
+10 °C	~2 d
+20 °C	~1 d
+30 °C	~1 d

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LIMITATIONS

- If Sikafloor®-81 EpoCem® ID is used as TMB (Temporary Moisture Barrier), a layer of a minimum 2 mm thick must be applied. (~4.5 kg/m²)
- Always ensure good ventilation when using Sikafloor®-81 EpoCem® ID in a confined space to remove excess moisture.
- Freshly applied Sikafloor®-81 EpoCem® ID must be protected from damp, condensation and water for at least 24 hours.
- Prevent premature drying by protecting from strong wind and do not expose to direct sun light while fresh.
- Apply primer and Sikafloor®-81 EpoCem® ID on a falling temperature. If applied during rising temperatures "pin holing" can occur.
- Applications under extreme conditions (high temperature and low humidity) which can cause fast drying of the product must be avoided as the product does not allow the use of curing compounds.
- Under no circumstances add water to the mix.
- The incorrect assessment and treatment of cracks can lead to a reduced service life and reflective cracking.
- Colour variations can occur on unsealed Sikafloor®-81 EpoCem® ID through exposure to direct sun light. This however, will not adversely influence the mechanical properties.
- When overlaying with PMMA screeds, the surface of Sikafloor®-81 EpoCem® ID must be fully broadcast with sand 0.4 - 0.7 mm.
- The TMB effect in Sikafloor®-EpoCem® is limited in time, without additional preparation.
- Sikafloor®-81 EpoCem® ID must be protected by subsequent coating on top within 5-7 days after application.
- Always verify the surface moisture content if more than 5-7 days have passed since application.

Non-moving construction joints require pre-treatment with a stripe of primer and Sikafloor®-81 EpoCem® ID.

Treat as follows:

- Static Cracks: Prefill and level with Sikadur® or Sikafloor® epoxy resin.
- Dynamic Cracks (> 0.4mm): To be assessed on site and if necessary apply a stripe coat of elastomeric material or design as a movement joint.
- The incorrect assessment and treatment of cracks can lead to a reduced service life and reflective

cracking.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet (MSDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

MIXING

Prior to mixing, shake Comp.A (white liquid) briefly until homogenous, then pour into container of Comp.B and shake vigorously again for at least 30 seconds. When dosing out of drums, stir and homogenise first. Pour the mixed binder mixture (A+B) into a suitable mixing container (capacity of about 30 litres) and gradually add Comp.C to the mixer while stirring with a power mixer. Mix thoroughly for 3 minutes until a uniform mix has been achieved with no lumps.

Mix only full units of A+B+C components. Do not mix smaller amounts. Do not add water.

When dosing with additional aggregates, add them after adding part C to the mix. Mix thoroughly for 3 minutes until a uniform mix has been achieved.

Mixing Tools:

Mix using a slow speed electric mixer (300 - 400 rpm) with helical paddle or other suitable equipment. For mixing 2 – 3 bags at once, single or counter rotating double mortar (basket type) and forced action (pan type) mixers are also recommended. Free fall mixers must not be used.

APPLICATION

Place mixed Sikafloor®-81 EpoCem® ID onto the primed substrate and spread evenly to the required thickness uniformly with a rubber or metal trowel or spatula and immediately roll with a spike roller to remove entrapped air and obtain an even thickness layer.

Workability can be adjusted by varying slightly the amount of Comp.C.

Do not use additional water, which would disturb the surface finish and cause discolouration.

A seamless finish can be achieved if a 'wet' edge is maintained during application.

CLEANING OF TOOLS

Clean all tools and application equipment with water and or thinner C immediately after use. Hardened /

cured material can only be removed mechanically.

MAINTENANCE

CLEANING

Due to the texture of its surface, Sikafloor®-81 EpoCem® ID is not suitable to be used as wearing layer where easy staining can occur. A seal coat of the Sikafloor® range with suitable cleaning capabilities is advisable. Remove dirt using a brush and/or vacuum. Do not use wet cleaning methods until the product is fully cured. Do not use abrasive methods or cleaners.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

SIKA HONGKONG LTD.

Rm.1507-12, Blk A, New Trade Plaza,
6 On Ping Street, Shatin, N.T., H.K.
Phone: +852 26868108
Fax: +852 26453671
Mail: marketing@hk.sika.com
Website: www.sika.com.hk



Product Data Sheet
Sikafloor®-81 EpoCem® ID
September 2023, Version 03.02
020814010020000019

Sikafloor-81EpoCemID-en-HK-(09-2023)-3-2.pdf