

PRODUCT DATA SHEET

Sikalastic® M 678

(formerly MSeal M 678)

Rapid curing, chemical resistant, elastomeric waterproofing membrane

DESCRIPTION

Sikalastic® M 678 is a solvent free, two component, high performance polyurea hybrid based waterproofing membrane, with high resistance to common chemicals. Using a specially designed spraying machine, the two components are pre- heated and spray applied, to a rapid curing, elastomeric, waterproofing membrane.

USES

Sikalastic® M 678 is recommended for waterproofing of large structures exposed to aggressive waters, containing potable water and other containment structures.

Typical application areas include:

- Water containment areas. Potable and contaminated
- Primary & Secondary containment tanks
- Waste water treatment tanks
- Protection & waterproofing of infrastructures.

CHARACTERISTICS / ADVANTAGES

- Fast reacting - Rapid installation. Does not run when applied on vertical surfaces
- Seamless - No risk of leaky seams and laps.
- Spray applied - Fast installation on large surfaces; easy application on complex details.
- Fully bonded - Eliminates water collection behind membrane even if punctured.
- High tensile strength - Excellent ability to accept movements without rupturing.
- Elastomeric - Excellent crack-bridging ability.
- High tear resistance - Minimised risk of damage to membrane in service.
- Low Tg (Glass Transition Temperature) of -20°C - Remains elastomeric at very low temperatures. Performance unaffected in below freezing conditions.
- Solvent-free - Improved safety.
- Potable water contact approved – suitable for tanks containing drinking water

PRODUCT INFORMATION

Chemical Base	Hybrid Polyurea	
Packaging	Sikalastic® M 678 Part A and B is supplied in 200kg drums.	
Shelf Life	12 months from date of production	
Storage Conditions	Store out of direct sunlight, clear of the ground on pallets protected from rainfall	
Density	Part A	1.03 kg/L (at 25°C)
	Part B	1.10 kg/L (at 25°C)
Viscosity	Part A	1000 ± 150 cps (at 25°C)
	Part B	1250 ± 200 cps (at 25°C)

TECHNICAL INFORMATION

Shore A Hardness	> 85	(DIN 53505)
Tensile Strength	>16 N/mm ²	(DIN 53504)
Elongation at Break	> 550 % (Elongation at break)	(DIN 53504)
Tear Strength	> 70 kg/cm	(ASTM D624)
Resistance to Weathering	No cracks ,No Delamination when tested for accelerated weathering in UV Chamber(QUV) for upto 1000 hrs	

SYSTEM INFORMATION

Mixing Ratio	Part A : Part B = 1:1 (By Volume)
Consumption	Sikalastic® M 678 is applied approximately at 1.05 –2.1 kg/m ² depending on the substrate.This corresponds to a cured film thickness(DFT) of approx. 1.0 – 2.0 mm. Details, corners require a higher coverage rate up to 4.0 kg/m ² or more.
Product Temperature	To be heated to 65-70 °C
Ambient Air Temperature	+10 °C min. / + 40 °C max.
Relative Air Humidity	Maximum upto 85 %
Dew Point	Beware of condensation. The substrate and uncured applied membrane must be at least +3 °C above dew point.
Substrate Temperature	+10 °C min. / + 40 °C max.
Substrate Moisture Content	≤ 4 % parts by weight.
Gel time	≈ 6-10 secs
Tack Free Time	≈ 60-120 secs

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet (MSDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

For detailed information on application, please obtain a copy of the “Application Guide for Sikalastic® M 678” from our Technical Services team.

Some tips for optimal performance

- For optimum chemical and mechanical performance thickness's greater than 1.5 mm should be used.
- For optimum spray results the material should be heated to 60-70 °C.
- Store Sikalastic® M 678 cool conditions in hot weather and warm conditions in cold weather.

- Repair voids, cracks and unevenness in substrates before application.
- Remove all surface contaminants and ensure substrate is dry.
- Avoid application during rain.
- Agitate Part A before application.
- Apply by spraying uniformly to recommended thickness using recommended spray machine.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The

user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

SIKA HONGKONG LTD.

Rm.1507-12, Blk A, New Trade Plaza,
6 On Ping Street, Shatin, N.T., H.K.
Phone: +852 26868108
Fax: +852 26453671
Mail: marketing@hk.sika.com
Website: www.sika.com.hk



Product Data Sheet

Sikalastic® M 678

October 2024, Version 02.02
02070600000002015

SikalasticM678-en-HK-(10-2024)-2-2.pdf

