

PRODUCT DATA SHEET

SikaProof®-612

PRE-APPLIED FULLY BONDED WATERPROOFING MEMBRANE FOR BASEMENT AND FOUNDATIONS

DESCRIPTION

SikaProof®-612 is a fully bonded, pre-applied sheet membrane waterproofing system for basement and foundation structures. It is two-layer composite membrane combined with existing single sheet layer (TPO polymer layer) and functional layer. SikaProof®-612 creates a strong chemical and mechanical bond to concrete, which prevent any lateral water migration.

USES

SikaProof®-612 may only be used by experienced professionals.

Waterproofing, damp-proofing and concrete protection for basements against ground water ingress. Suitable for use on:

- Reinforced concrete base slabs
- Extension and reconstruction works

PRODUCT INFORMATION

Chemical Base	Polymer layer: Sheet layer Functional layer: PSA / quartz sand layer
Packaging	SikaProof®-612 standard rolls are wrapped individually in a knitted plastic bag. 1.00 m (width) x roll length 20 m 2.00 m (width) x roll length 20 m
Appearance / Colour	Sheet layer: Smooth / White Function layer: Rough
Shelf Life	SikaProof®-612 have a shelf-life of 12 months from date of production.
Storage Conditions	Product must be stored in original unopened and undamaged sealed packaging in dry conditions and temperatures between + 5°C and +35°C, Store in a horizontal position. Do not stack pallets of the rolls on top of each other, or under pallets of any other materials during transport or storage. Do not stack

rolls more than 5 layers.
Always refer to packaging.

Effective Thickness	1.2mm (-5% / +10%) (Sheet layer 0.9 mm / function layer 0.3 mm)	EN 1849-2
Resistance to Impact	400 mm	EN 12691
Tensile Strength	≥16 MPa	GB/T 23457
Elongation	≥ 400 %	GB/T 23457
Tear Strength	≥ 400 N	GB/T 23457
Joint Shear Resistance	450 ± 10% \square N/50mm)	(EN12317-2)
Foldability at Low Temperature	Main Material -35°C no cracks No crack at -30°C	GB/T 23457 ASTM D1970
Water Tightness	0.3 MPa 120min watertight	GB/T 23457
Adhesion in Peel	≥ 1.5 N/mm no treatment (with concrete substrate)	GB/T 23457
Resistance to Lateral Water Migration	Pass, up to 7 bar (71m)	ASTM D5385, modified

APPLICATION INFORMATION

Substrate Temperature +5 °C min. / +60 °C max.

SYSTEM INFORMATION

System Structure The following system products must be used in pre-applied system:

- SikaProof®-612 sheet membrane
- SikaProof® Tape 80 AP for detailing or optional for internal jointing

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LIMITATIONS

Installation work must only be carried out by Sika trained, approved or competent contractors experienced in this type of application
Reference must also be made to the Sika Method Statement: SikaProof®-6xx Series for more detailed information

- Do not install SikaProof®-612 membrane during continuous or prolonged rain, snowfall or sandstorm.
- The substrate application surface must be clean with no standing water
- Additional Sika Joint Sealing Solutions (minimum SikaSwell®) must be used for connection around penetrations and for construction joints.
- Concrete must be placed within 14 days after membrane installation
- Proper concrete installation (workmanship and mix design) is the key for the fully bonding properties
- Do not install SikaProof®-612 on structures where it will be permanently exposed to UV light
- Substrate: In case that the substrate is not

smooth use Geotextile 300-1000 g/m² to protect the SikaProof®-612 from sharp elements of the blinding concrete.

ECOLOGY, HEALTH AND SAFETY

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

SikaProof®-612 membrane must be applied on a sufficiently stable, well compacted (blinding layer) substrate to avoid movement during the construction works. Substrate surface must be smooth, uniform and clean. Substrate can be damp, slightly wet or ponding water must be avoided.

APPLICATION METHOD / TOOLS

Follow Sika Method Statement: SikaProof®-6xx Series

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data

Sheet for the exact description of the application fields.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

SIKA HONGKONG LTD.

Rm.1507-12, Blk A, New Trade Plaza,
6 On Ping Street, Shatin, N.T., H.K.
Phone: +852 26868108
Fax: +852 26453671
Mail: marketing@hk.sika.com
Website: www.sika.com.hk



Product Data Sheet

SikaProof®-612

July 2026, Version 03.01
02072030110000020

SikaProof-612-en-HK-(07-2026)-3-1.pdf