

PRODUCT DATA SHEET

SikaCor® EG-4

2-PACK AY-PUR TOP COAT CONTAINING MICACEOUS IRON OXIDE

DESCRIPTION

SikaCor® EG-4 is a 2-pack acrylic polyurethane top coat containing micaceous iron oxide pigments (MIO).
By adding 1 % b.w. SikaCor® PUR Accelerator (see product data sheet for more information) a faster touch-drying and full curing will be achieved.

USES

SikaCor® EG-4 may only be used by experienced professionals.
In combination with 2-pack primer and intermediate coats of the SikaCor® and Sika® Permacor® product range for heavy duty corrosion protection of steel structures.

CHARACTERISTICS / ADVANTAGES

Combined with 2-pack epoxy primer and intermediate coats:

- Very good corrosion protection
- Excellent chemical, weather and colour stability
- Tough elastic and hard but not brittle
- Insensitive against shock and impact

APPROVALS / STANDARDS

- Approved according to German standard 'TL/TP-KOR-Stahlbauten', page 87 and page 94.
- In combination with SikaCor® PUR Accelerator, SikaCor® EG-4 is approved according to German standard 'TL/TP-KOR-Stahlbauten', page 97.

PRODUCT INFORMATION

| | | |
|----------------------------|--|-----------------------|
| Packaging | SikaCor® EG-4 | 30 kg and 12.5 kg net |
| | Sika® Thinner EG | 25 L, 10 L and 3 L |
| | SikaCor® Cleaner | 25 L |
| Appearance / Colour | Metallic shades acc. DB standard Slight colour deviations are possible due to raw material characteristics. | |
| Shelf Life | 2 years | |
| Storage Conditions | In originally sealed containers in a cool and dry environment. | |
| Density | ~ 1.4 kg/L | |
| Solid Content | ~ 55 % by volume | |
| | ~ 70 % by weight | |

TECHNICAL INFORMATION

| | |
|----------------------------|--|
| Chemical Resistance | Weather, water, sewage, seawater, smoke, de-icing salts, acid and lye vapours, oils, grease and short term exposure to fuels and solvents. |
| Thermal Resistance | Dry heat up to +150 °C, short term up to +180 °C Damp heat up to approx. +50 °C |

SYSTEM INFORMATION

| | |
|----------------|--|
| Systems | <u>Steel:</u> Used as top coat on 2-pack primer and intermediate coats of the SikaCor® and Sika® Permacor® product range. <u>Hot dip galvanized steel, stainless steel and aluminium:</u> 1 x SikaCor® EG-1 or SikaCor® EG-1 VHS 1 x SikaCor® EG-4 |
|----------------|--|

APPLICATION INFORMATION

| | | | | |
|---|---|--|--------------|--|
| Mixing Ratio | | Components A : B | | |
| | By weight | 92 : 8 | | |
| | By volume | 8.9 : 1 | | |
| Thinner | Sika® Thinner EG If necessary max. 5 % Sika® Thinner EG may be added to adapt the viscosity. | | | |
| Consumption | Theoretical material-consumption/VOC without loss for medium dry film thickness: | | | |
| | Dry film thickness | 80 µm | | |
| | Wet film thickness | 145 µm | | |
| | Consumption | ~ 0.205 kg/m ² | | |
| Product Temperature | Min. + 5 °C | | | |
| Relative Air Humidity | Max. 85 %, except the surface temperature is significantly higher than the dew point temperature, it shall be at least 3 K above dew point. The surface must be dry and free from ice. | | | |
| Substrate Temperature | Min. + 5 °C 0 °C by adding SikaCor® PUR Accelerator | | | |
| Pot Life | At +10 °C | ~ 7 h | ~ 5 h * | |
| | At +20 °C | ~ 5 h | ~ 3 h * | |
| | At +30 °C | ~ 4 h | ~ 2 h * | |
| * By adding 1 % b.w. SikaCor® PUR Accelerator | | | | |
| Drying Stage 6 | | Dry film thickness 80 µm | (ISO 9117-5) | |
| | +5 °C after | 19 h | | |
| | +10 °C after | 16 h | | |
| | +20 °C after | 12 h | | |
| | +40 °C after | 1.5 h | | |
| | +80 °C after | 20 min | | |
| | | By adding 1 % b.w. SikaCor® PUR Accelerator: | | |
| | | Dry film thickness 80 µm | (ISO 9117-5) | |
| | 0 °C after | 48 h | | |
| | +5 °C after | 16 h | | |
| +10 °C after | 12 h | | | |
| +20 °C after | 4 h | | | |

Waiting Time / Overcoating

Min. until drying stage 6 is achieved
 Max. unlimited
 Prior to further applications possible contamination must be removed.

Drying Time

Final drying time
 Depending on film thickness and temperature full hardness is achieved after 1–2 weeks. Tests of the completed coating system should only be carried out after final curing.

APPLICATION INSTRUCTIONS**SURFACE PREPARATION**Steel:

Blast cleaning to Sa 2 ½ according to ISO 12944-4.
 Free from dirt, oil and grease.

Hot-dip galvanized steel, stainless steel and aluminium:

Free from dirt, oil, grease and corrosion products.
 In case of permanent immersion and condensation the surfaces must be slightly sweep blasted with non-ferrous abrasives.

For contaminated surfaces e.g. galvanized or primed areas we recommend to clean with SikaCor® Wash.

MIXING

Stir component A very thoroughly using an electric mixer (start slowly, then increase up to approx. 300 rpm). Add component B carefully and mix both components very thoroughly (including sides and bottom of the container). Mix for at least 3 minutes until a homogeneous mixture is achieved. Fill mixed material into clean container and mix again shortly as described above. During mixing and handling of the materials always wear protective goggles, suitable gloves and other protective clothing.

APPLICATION

The method of application has a major effect on achieving uniform thickness and appearance. Spray application will give the best results. The indicated dry film thickness is easily achieved by airless spray. Adding solvents reduces the sag resistance and the dry film thickness. In case of application by roller or brush, additional applications may become necessary to achieve the required coating thickness, depending on type of construction, site conditions, colour shade etc. Prior to major coating operations a test application on site may be useful to ensure the selected application method will provide the requested results.

By brush and roller:

In order to achieve an attractive appearance in case of coatings containing micaceous iron oxide it is recommended to spray apply the last top coat or to brush or roll on in one direction only to avoid streaking.

Conventional high pressure spraying:

- Nozzle size 1.5–2.5 mm
- Pressure 3–5 bar
- Oil and water trap is compulsory

Airless-spraying:

- Pressure min. 180 bar
- Nozzle size 0.38–0.53 mm (0.015–0.021 inch)
- Spraying angle 40°–80°

CLEANING OF TOOLS

SikaCor® Cleaner
 Spraying equipment must be rinsed with Sika® Thinner EG before using SikaCor® EG-4.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet (MSDS) containing physical, ecological, toxicological and other safety-related data.

VOC DATA

VOC content (ready to use) not exceeding 500 gm/litre [Type of regulated paint under the Air Pollution Control (volatile organic compounds) Regulation of Hong Kong: (metallic pigmented coatings)].

The maximum content of SikaCor® EG-4 is < 500 gm/litre VOC for the ready to use product.



LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

SIKA HONGKONG LTD.

Rm.1507-12, 15/F, Block A,
New Trade Plaza,
6 On Ping Street,
Shatin, N.T.
Hong Kong.



Product Data Sheet
SikaCor® EG-4
November 2018, Version 05.01
020602000040000003

SikaCorEG-4-en-HK-(11-2018)-5-1.pdf