

SYSTEM DATA SHEET

Sikafloor® MultiDur EB-56 ESD

Slip-resistant, conductive epoxy ESD flooring system

DESCRIPTION

Sikafloor® MultiDur EB-56 ESD is an epoxy ESD flooring system with a slip resistant textured finish. The system is designed to dissipate electrostatic charges (ESD) and protect sensitive equipment in electrostatic protected areas (EPA).

USES

Sikafloor® MultiDur EB-56 ESD may only be used by experienced professionals.

Sikafloor® MultiDur EB-56 ESD is used in industrial buildings such as:

- Automotive facilities
- Electronic facilities and data centres
- Pharmaceutical facilities

Please note:

- The System may only be used by experienced professionals.
- The System may only be used for interior applications.

CHARACTERISTICS / ADVANTAGES

- Provides reliable and long-lasting ESD protection
- Functional finish with slip-resistant properties
- Good resistance to specific chemicals
- Electrostatically conductive
- Very good mechanical resistance
- Low VOC emissions
- Low Airborne Molecular Contaminants (AMC) emissions


APPROVALS / STANDARDS

- Determination of anti-slip properties DIN 51130, TZUS, Report No. 030-062173
- Fire Classification report EN 13501-1, GHENT, Report No. CR 21-0970-01

SYSTEM INFORMATION

System Structure

Sikafloor® MultiDur EB-56 ESD



Layer	Product
1. Primer	Sikafloor®-150 Plus Sikafloor®-156 Sikafloor®-161 Contact Sika Technical Service for information on choosing the right primer for your project.
2. Conductive primer	Sikafloor®-2017 Earthing Kit Sikafloor®-220 W Conductive
3. Conductive wearing layer	Sikafloor®-2350 ESD filled 20 % with Quartz sand (0.1–0.3 mm) Broadcast in excess with one of the following: Silicone carbide (0.5-1.0) mm Quartz Sand (0.3–0.8 mm) Quartz Sand (0.6–1.2 mm)
4. Top coat	Sikafloor®-2350 ESD

Composition	Epoxy
Colour	Available in the Ral colours,contact Sika Technical Service for information on choosing the colours.
Nominal thickness	2 mm to 3 mm

TECHNICAL INFORMATION

Tensile Adhesion Strength	≥ 1.5 MPa	(EN 1542)
Chemical Resistance	Laboratory-defined resistance to many individual chemicals. Before proceeding, contact Sika Technical Service for specific information.	
Electrostatic Behaviour	Resistance to ground	$R_g < 10^9 \Omega$ (IEC 61340-4-1)
	Typical average resistance to ground	$R_g < 10^5-10^6 \Omega$
	Body voltage generation	< 100 V (IEC 61340-4-5)
	System resistance	$R_g < 10^9 \Omega$

ESD MEASUREMENT CONDITIONS AND SPECIFICATIONS

All measurement values for the system stated in the System Data Sheet (except those referring to proof statements) were measured using the following equipment and ambient conditions:

Condition or Equipment	Specification
Size of ESD-footwear	42 (EU) (UK: 8; US: 8.5)
Test person weight	90 kg
Ambient conditions	+23 °C and 50 % relative humidity
Measuring device for measuring resistance to ground	Metriso 2000 or 3000 (Warmbier) or comparable
Surface resistance probe	Carbon Rubber electrode. Weight: 2.50 kg
Rubber pad hardness	Shore A (60 ±10)
Measuring device for measuring body voltage generation	Walking Test Kit WT 5000 (Warmbier) or comparable

IMPORTANT

ESD footwear requirements

The ESD shoes used in the EPA must have a resistance of < 5 MOhm according to IEC 61340-4-3 at climate class 1 (12 % relative humidity and +23 °C). In order to achieve charges of < 30 volts of human body charge during the walking test (at 12 % relative humidity and +23 °C), we recommend using the following ESD shoes: Weeger ESD clog, art. 48512-30, www.schuh-weeger.de.

Note: Measurement results can be affected by ESD clothing, ambient conditions, measurement equipment, cleanliness of the floor and the test personnel.

APPLICATION INFORMATION

Consumption	Layer	Product	Consumption
	Primer	Sikafloor®-150 Plus Sikafloor®-156 Sikafloor®-161	1-2 × 0.3–0.5 kg/m ²
	Conductive primer	Sikafloor®-2017 Earthing Kit Sikafloor®-220 W Conductive	1 earthing point per 200–300 m ² , minimum 2 per room. 0.08–0.10 kg/m ²
	Conductive wearing layer	Sikafloor®-2350 ESD filled 20 % with Quartz sand (0.1–0.3 mm) Broadcast in excess with one of the following: Silicone carbide (0.5–1.0) mm Quartz Sand (0.3–0.8 mm) Quartz Sand (0.6–1.2 mm)	1.1 kg/m ² (resin) 4–6 kg/m ² (broadcast)
	Top coat	Sikafloor®-2350 ESD	0.75–0.85 kg/m ²

Note: Consumption data is theoretical and does not allow for any additional material due to surface porosity, surface profile, variations in level, wastage or any other variations. Apply the Product to a test area to calculate the exact consumption for the specific substrate conditions and proposed application equipment.

Ambient Air Temperature	Maximum	+30 °C
	Minimum	+15 °C
Relative Air Humidity	Maximum	80 % r.h.

SYSTEM DATA SHEET

Sikafloor® MultiDur EB-56 ESD
September 2026, Version 08.01
020811900000000189

BUILDING TRUST



Dew Point	Refer to the individual Product Data Sheet.			
Substrate Temperature	Maximum	+30 °C		
	Minimum	+15 °C		
Substrate Moisture Content	Refer to the individual Product Data Sheet.			
Waiting Time / Overcoating	For the waiting time to overcoating of the primer, refer to the individual Product Data Sheet.			
	Before applying Sikafloor®-2350 ESD on Sikafloor®-220 W Conductive, allow:			
	Temperature	Minimum	Maximum	
	+15 °C	26 hours	7 days	
	+20 °C	17 hours	5 days	
	+30 °C	12 hours	4 days	
	Note: Times are approximate and will be affected by changing ambient conditions, particularly temperature and relative humidity.			
Applied Product Ready for Use	Temperature	Foot traffic	Light traffic	Full cure
	+10 °C	48 hours	3 days	7 days
	+20 °C	24 hours	48 hours	4 days
	+30 °C	16 hours	36 hours	3 days
Note: Times are approximate and will be affected by changing ambient conditions, particularly temperature and relative humidity.				

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER DOCUMENTS

Refer to the following method statements:

- Sika Method Statement — Evaluation and preparation of surfaces for flooring systems
- Sika Method Statement — Sikafloor® mixing and application

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet (MSDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

APPLICATION

ESD CONDUCTIVITY MEASUREMENTS

Recommended number of conductivity measurements is specified in the following table:

Ready applied area	Number of measurements
< 10 m ²	6
≥ 10 m ² and < 100 m ²	10 to 20
≥ 100 m ² and < 1000 m ²	50
≥ 1000 m ² and < 5000 m ²	100

If the measurements yield values that are outside of

the agreed specification, follow these steps:

1. Carry out one additional measurement within a radius of approximately 30 cm around the original measuring point.

If the value of the new measurement meets the agreed specification, the original measurement can be disregarded.

If the value of the new measurement does not meet the agreed specification, repeat the measurement described above until the fulfilment of the requirements have been verified.

If the requirements cannot be verified, contact Sika Technical Services.

INSTALLATION OF EARTHING POINTS

Refer to Sika Method Statement: Sika Method Statement — Sikafloor® mixing and application

Number of earthing connections per room: Minimum of 2 earthing connections. The optimum number of earthing connections depends on the local conditions and must be specified on drawings or other contract documentation.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

SYSTEM DATA SHEET

Sikafloor® MultiDur EB-56 ESD
September 2026, Version 08.01
020811900000000189

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

SIKA HONGKONG LTD.

Rm.1507-12, Blk A, New Trade Plaza,
6 On Ping Street, Shatin, N.T., H.K.
Phone: +852 26868108
Fax: +852 26453671
Mail: marketing@hk.sika.com
Website: www.sika.com.hk



SYSTEM DATA SHEET

Sikafloor® MultiDur EB-56 ESD
September 2026, Version 08.01
020811900000000189

SikafloorMultiDurEB-56ESD-en-HK-(09-2026)-8-1.pdf