

BUILDING TRUST

PRODUCT DATA SHEET

Sikafloor® QuartzTop-135

(formerly MTop 135)

Dry-shake surface hardener based on mineral aggregates for application by laser technique.

DESCRIPTION

Sikafloor® QuartzTop-135 is a ready to use pre-mixed surface hardener, applied by laser screed. Sikafloor® QuartzTop-135 contains hydraulic binder and special graded mineral aggregate.

Please note: The Product may only be used by experienced professionals only.

USES

Sikafloor® QuartzTop-135 is recommended for industrial floors with medium to moderate traffic in:

- basements
- mechanical workshops
- garages for passenger cars
- storage rooms
- corridors, halls
- educational facilities
- shopping centers, parking area

CHARACTERISTICS / ADVANTAGES

Sikafloor® QuartzTop-135 offers following advantages:

- High abrasion resistance (twice as much as normal concrete floor)
- A very dense surface
- Low level of porosity due to maximum compactness
- Easy to clean
- Limited dust formation
- Optimized formulation for application via laser screed equipment

APPROVALS / STANDARDS

CE marking and declaration of performance based on EN 13813:2002 Screed material and floor screeds — Screed material — Properties and requirements — Cementitious screed material

PRODUCT INFORMATION

Packaging	Sikafloor® QuartzTop-135 is packaged in 25 kg moisture resistant bags and big-bags	
Appearance / Colour	ready to use grey powder cementgrey, colors see color-chart	
Shelf Life	Sikafloor® QuartzTop-135 can be stored for 18 months in the tightly closed original packages. Do not use the product if bag is damaged.	
Storage Conditions	The Product must be stored in original, unopened and undamages sealed packaging in dry conditions at temperature between +5°C and +30°C. Always refer to the packaging. Kept frost-free and dry.	
Grain size distribution	0 – 3,15 mm	
pH-Value	> 12	

Product Data Sheet

Sikafloor® QuartzTop-135October 2024, Version 02.01
020815000000002041

TECHNICAL INFORMATION

Abrasion Resistance	BCA	AR1 (max. 100 μm wear depth)	(EN 13892-4)
	ВОНМЕ	A6 (max. 6 cm ³ / 50 cm ²)	(EN 13892-3)
	TABER	0,28 g / 1000 rev CS-17	(ISO 5470-1)
	AMSLER	2,88 mm / 3.000 m	(NBN-15-223)
Resistance to Impact	Class I	On concrete block MC 0,40 acc. EN 17	'66(EN ISO 6272-1))
Compressive Strength	> 60 N/mm² (nominal 70 N/mm²)		(EN 13982-2)
Modulus of Elasticity in Compression	35 kN / mm ²		(EN 13412)
Tensile Strength in Flexure	10 N/mm²		(EN 13982-2)
Tensile Adhesion Strength	2,7 N/mm² (concrete fail- ure)		(EN 13892-8)
	class > B 2,0	On concrete	
Reaction to Fire	A1 _{fl}		

APPLICATION INFORMATION

Consumption	For light to medium traffic: 4 kg/m ² For medium to heavy traffic: 5,5 –
	8 kg/m ² For heavy traffic: 7 – 8 kg/m ²

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LIMITATIONS

- Where operating and service conditions dictate the use of a metallic aggregate surface hardener for greater abrasion and impact resistance.
- For use in areas exposed to acids and their salts or to materials known to deteriorate cement concrete, consult your local representative.
- Do not apply over concrete with > 3% entrained air.

ECOLOGY, HEALTH AND SAFETY

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in the product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0,1 % (w/w).

APPLICATION INSTRUCTIONS

APPLICATION

- 1. Placing concrete
- 2. Levelling, consolidating and striking off concrete
- 3. Application of Sikafloor® QuartzTop-135 with laser screed
- 4. Floating the shake of Sikafloor® QuartzTop-135 followed by a first trowelling and a second/final trowelling
- 5. Curing
- 6. Sawing joints
- 7. Application of joint sealant

For detailed information on the application steps, please consult with Sika technical support or local representatives.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.



Sikafloor® QuartzTop-135October 2024, Version 02.01
020815000000002041



LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

SIKA HONGKONG LTD.

Rm.1507-12, Blk A, New Trade Plaza, 6 On Ping Street, Shatin, N.T., H.K. Phone: +852 26868108 Fax: +852 26453671 Mail: marketing@hk.sika.com Website: www.sika.com.hk





Product Data Sheet Sikafloor® QuartzTop-135 October 2024, Version 02.01 020815000000002041 SikafloorQuartzTop-135-en-HK-(10-2024)-2-1.pdf

