

## PRODUCT DATA SHEET

# Ronabond® Premixed Render

Hand or Spray Applied Polymer Enhanced High Build Render

### DESCRIPTION

Ronabond® Premixed Render is a polymer enhanced mortar with waterproofing function designed for internal and external render applications. Ronabond® Premixed Render is pre-bagged ensuring correct mixing proportions which avoids possible mixing errors on site. Ronabond® Premixed Render is suitable for hand or spray application and can be applied to a variety of substrates.

### USES

- Blockwork
- Brickwork
- Internal and external concrete substrates
- Drywall
- Fair faced concrete
- Internal & external application

### CHARACTERISTICS / ADVANTAGES

- Premixed for quality control
- Sprayable
- Excellent bonding characteristics
- Improved workability
- High build properties
- Low VOC

### PRODUCT INFORMATION

Packaging	25 kg bag
Appearance / Colour	Concrete grey
Shelf Life	9 months from the date of production.
Storage Conditions	Stored properly in undamaged and unopened original sealed packaging. Protect from direct sunlight and frost.

### TECHNICAL INFORMATION

Compressive Strength	25 MPa @ 28 days		
Tensile Strength	2.6 MPa @ 28 days		
Shrinkage	Age at Test	Ronabond® Premixed Render Typical Performance	Test Method
	1 & 28 days	No crack between 1 & 28 days	Coutinho Ring (TM6)

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet (MSDS) containing physical, ecological, toxicological and other safety-related data.

## APPLICATION INSTRUCTIONS

### SUBSTRATE QUALITY / PRE-TREATMENT

The substrate on which Ronabond® Premixed Render is being placed must be structurally sound and stable and suitable to receive and support a render. All grease, oil, dirt and deleterious material must be removed. Substrate should be pre-wetted to a damp condition before rendering. If the render is applied by hand, we recommend a brush coat of Ronafix® Bond Coat onto a damp substrate before applying the render.

### MIXING

Mix using a forced action mixer or using a slow speed drill and paddle. Place the whole bag of powder into the mixing vessel and add approximately 4 litres of clean water. Mix for 3–5 minutes to achieve a homogeneous workable mortar.

### APPLICATION

Ronabond® Premixed Render can be applied up to 50 mm thickness in a single application.

### Pumping / Spraying:

To pump or spray Ronabond® Premixed Render, a continuous mixing and pumping machine should be utilized for both mixing and spraying. Ronabond® Premixed Render is continuously fed into the mixing machine hopper and mixed with clean water

to provide a homogeneous workable mortar.

### CLEANING OF TOOLS

Clean all tools and application equipment with clean water immediately after use.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

### SIKA HONGKONG LTD.

Rm.1507-12, Blk A, New Trade Plaza,  
6 On Ping Street, Shatin, N.T., H.K.  
Phone: +852 26868108  
Fax: +852 26453671  
Mail: marketing@hk.sika.com  
Website: www.sika.com.hk



Product Data Sheet  
Ronabond® Premixed Render  
December 2024, Version 03.02  
020302050010000095

RonabondPremixedRender-en-HK-(12-2024)-3-2.pdf