

## PRODUCT DATA SHEET

# SikaInject®-315 PS

(formerly TPH.® POLINIT)

Polymeric strengthening (PS) compound for SikaInject® Acrylate Resins

### DESCRIPTION

SikaInject-315 PS is a polymeric strengthening compound for the acrylate resin SikaInject-304 DE. PS compound is used instead of water for preparation of component B. Use with further SikaInject-3\*\* acrylate resins on request.

### USES

SikaInject®-315 PS may only be used by experienced professionals.

- Sealing of cracks, joints and cavities in concrete, masonry or in the ground
- Sealing of all types of leaking building components in damp or water saturated ground
- Filling/sealing of annular gaps in tunneling or shaft structures
- Repair of waterproofing membranes e.g. in tunnels or basements
- Repair of expansion joints e.g. failed waterbars
- Curtain Injection

### CHARACTERISTICS / ADVANTAGES

- Permanently elastic
- watertight up to 7 bar
- Increase of flexibility
- Increase of adhesion on siliceous surfaces
- Reduction of shrinkage in case of ventilation
- CE-certified (EN 1504-5)
- Resistant to alternating freeze and thaw exposure
- Once cured, the product is insoluble in water and hydrocarbons and resistant to alkalis

### APPROVALS / STANDARDS

- CE-Mark, DOP, concrete injection for (S) filling of cracks, joints, honeycombs acc. to EN 1504-5
- Renovation of defective expansion joints; MFPA Leipzig
- Resistance test to freeze-thaw cycling; MFPA Leipzig
- Resistance test to concrete-corrosive fluids; MFPA Leipzig
- Watertightness-Test 7 bar, acc. to DIN EN 14068; MFPA Leipzig
- Tested with SikaInject®-304 DE

### PRODUCT INFORMATION

Packaging	20 kg Larger packaging on request.
Colour	white, liquid
Shelf Life	12 months in original packaging
Storage Conditions	dry, between 15-25°C, protected from heat, frost and direct sunlight
Density	~1.01 kg/l (DIN EN ISO 3675)
Viscosity	8 - 15 mPas (DIN EN ISO 2555)

### TECHNICAL INFORMATION

<b>Modulus of Elasticity in Flexure</b>	~ 0.49 MPa (DIN EN ISO 527) with SikalInject®-304 DE
<b>Tensile Strength</b>	~ 0.16 MPa (DIN EN ISO 527) with SikalInject®-304 DE
<b>Water Absorption</b>	~ 40 % (DIN EN ISO 62) with SikalInject®-304 DE
<b>Elongation at break</b>	~ 710 % (DIN EN ISO 527) with SikalInject®-304 DE

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## FURTHER DOCUMENTS

SikalInject®-315 PS can also be used in combination with other SikalInject®-3\*\* acrylate resins. Reaction and performance data can be found in the respective product data sheet.

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheets (SDS) containing physical, ecological, toxicological and other safety-related data.

## APPLICATION INSTRUCTIONS

### MIXING

SikalInject®-315 PS is used instead of water for preparing component B of SikalInject®-304 DE. At least 3 minutes of mixing are required for dissolving the part B (salt). The component B prepared in this way is ready-for-use and remains stable for ~ 5 hours (depending on temperature). The product is pumped in a mixing ratio of 1 : 1 (parts by volume, A : B) using a 2-component injection pump.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of Sika® Corporate Legal in Baar.

### SIKA HONGKONG LTD.

Rm.1507-12, Blk A, New Trade Plaza,  
6 On Ping Street, Shatin, N.T., H.K.  
Phone: +852 26868108  
Fax: +852 26453671  
Mail: marketing@hk.sika.com  
Website: www.sika.com.hk



Product Data Sheet  
SikalInject®-315 PS  
February 2026, Version 01.02  
020707020030000018

SikalInject-315PS-en-HK-(02-2026)-1-2.pdf